

TECHNICAL DATA SHEET

fluteck[®] P1050 Modified PTFE Standard Grade

Product Description.

fluorseals™ fluteck™P1050 Modified PTFE Standard Grade is Modified PTFE for Ram Extrusion, Compression and Isostatic moulding.

Product Properties:

- Improved mechanical properties
- Exceptional temperature resistance
- High limiting oxygen index
- Reduced deformation under load
- Higher transparency
- Excellent chemical resistance.
- Excellent electrical insulating properties
- Reduced friction & wear; Low friction behaviour
- Suitable for food contact
- Improved weldability

Property	Method	Units	Specification	
Physical	Color	-	White	
	Specific gravity	ASTM D792	g/cm ³	2,130 – 2,180
	Water absorption	ASTM D570	%	0,01
	Flamability	UL 94		V-0
Mechanical	Tensile strength	ASTM D4894	MPa	≥ 28
	Elongation	ASTM D4894	%	≥ 400
	Hardness	ASTM D2240	Shore D	≥ 54
	Ball Hardness	ASTM D785	MPa	≥ 23
	Compression strength at 1% deformation	ASTM D695	MPa	≥ 4
	Deformation under load (140 Kg/cm ² for 24 hrs. At 23° C)	ASTM D621	%	9 – 12
	Permanent deformation (after 24 hrs. Relaxation at 23° C)	ASTM D621	%	4,5 – 6
	Coefficient of static friction	ASTM D1894		0,08 – 0,10
	Coefficient of dynamic friction	ASTM D1894		0,06 – 0,08
	Wear factor K	ASTM D3702		2.900
	Wear coefficient		cm ³ min 10 ⁻⁸ Kg m h	20000 - 25000
Thermal	Thermal conductivity	ASTM C177	W/ m·K	0,24
	Coefficient of linear thermal expansion From 25 to 100 °C	ASTM D696	10 ⁻⁵ / °C	12 - 14
Electrical	Dielectric Strength	ASTM D149	kV /mm	≥ 50
	Volume resistivity	ASTM D257	Ohm·cm	10 ¹⁸
	Surface resistivity	ASTM D257	Ohm	10 ¹⁷

TECHNICAL DATA SHEET

Typical properties.

fluteck™P1050 is a Modified PTFE Standard Grade preferred for parts and components requiring very good mechanical properties.

fluteck™P1050 offers an excellent combination of properties typical of the fluoropolymer resins:

- Service Temperature: fluteck™P1050 offers excellent resistance to continuous service temperatures – working conditions from -100° C (-148°F) up to 250° C (482°F) and, for limited periods, even to higher temperatures; Product's low temperature resistance allows satisfactory performance down to -200° C (-328°F).
- Chemical resistance: fluteck™P1050 offers high inertness towards nearly all known chemicals. Only attacked elemental alkali metals, chlorine trifluoride and elemental fluorine at high temperature and pressures might affect properties.
- Solvents resistance: fluteck™P1050 offers insoluble properties in all solvents up to temperatures as high as 300° C (572° F). Certain highly fluorinated oils only swell and dissolve PTFE at temperatures close to the crystalline melting point.

Typical Application.

fluteck™P1050 Modified PTFE Standard Grade increases the already wide range of applications of virgin PTFE. Lower permeability to gases and deformation under load, greater elastic recover and mechanical properties and better weldability open up entirely new possibilities of applications in several fields such as Chemical, Electrical and Electronic, Petrochemical, Automotive, Mechanical, Medical, Aeronautics, Semiconductor and Food industry.

fluteck™P1050 Modified PTFE Standard Grade is ideal for use in applications that required high standard of safety and reliability, such as plant and machinery for high purity chemicals, semiconductor industry, analytical laboratories of food industry

Statement on suitability for contact with foodstuff.

FDA Approved US Regulation

- Code of Federal regulation 21 CFR Ch.1; section 177.1550 Perfluorocarbon Resins of the Food and Drug Administration/US.

EU Regulation

- EU 1935/2004 - 10/2011 on plastic materials and articles to come in contact with food.

Storage and Handling.

fluteck™P1050 Modified PTFE Standard Grade can be stored for a long period of life and is exceptionally resistant to aging and weather conditions up to 10 years. Specific aging tests carried out on sample exposed to aging and atmospheric conditions, showed no changes in weight and volume. In case of semi-finished products, before processing or before the machining, it is advisable to store the material for 24 hours in the production area, preferable in a clean and dry place at a temperature of less than 25°C (77°F), preferably between 21-25°C (70-77°F). This is very important when room temperature is low; in such cases the material should be conditioned up to 72 hours in the production area in the recommended temperature range.

Safety instruction.

Follow the normal precautions observed with all fluoropolymer materials.

Please consult the Material Safety Data Sheet and Product Label for information regarding the safe handling of the material. By following all precautions and safety measures, processing, machining, and using these products poses no known health risks. General handling and processing precautions include: 1) Process only in well-ventilated areas. 2) Do not smoke in working areas. 3) Avoid eye contact. 4) Avoid mouth contact. 5) If skin comes into contact with these products during handling, wash with soap and water afterwards. 6) Avoid contact with hot fluoropolymers.

The user must verify that the finished parts, made out of the semi-finished product, are technically suitable for the requested application. The user must also verify that the finished item may not cause any modification to the organoleptic properties of the foodstuff and that the item's technological fitness it is assigned to may be guaranteed.

For each foreign country market, where the articles are introduced into, it is user's responsibility to verify whether both material than articles comply with the applicable laws and regulations.

Delivery format.

fluteck™P1050 Modified PTFE Standard Grade is supplied in the following shapes and formats:

Semi-finished products: rods, tubes, sheets, tapes, strips. Shapes and sizes as per fluorseals™ General Size List and/as per customer request.

Machined parts: Shapes and sizes as per customer request.

Note: The information contained in this technical data sheet have been collected and ranked on technical data coming from reliable statistic series gathered in the field over the years. All information are intended only as general guidelines for use at user discretion. Fluorseals do not guarantee any specific result and do not assume any liability in connection with the use of the products in the described application. None of the information included in this document is to be taken as a licence to operate under, or recommendations to infringe any existing patents. Before the use, the product has to be sampled and tested in the specific application and in the field of use at working condition in order to be approved by the us

Rev: 03/2015



fluorseals spa®

Company Quality System UNI EN ISO 9001:2008 cert. CISQ/IIP N°061 First issue 1994
24064 Grumello del Monte BG Italy - Via Tribolina 20/22 - Tel. +39 035 4492811 - Fax +39 035 831410 - www.fluorseals.it - info@fluorseals.it